



1. COMPACT ALL A.C. LIFTS TO 91% OPTIMUM DENSITY PER RICE STANDARD METHOD.
2. ASPHALT EMULSION TACK COAT SHALL BE USED TO SEAL THE HMAC TO THE EDGES OF THE EXISTING AC PAVEMENT. ALL AC PAVEMENT CUTS SHALL BE VERTICAL, CLEAN & ASPHALT SAND SEALED ALONG ALL EDGES AFTER INSTALLATION.
3. ALL PAVEMENT CUT AREAS SHALL BE COLD PATCHED OR PLATED AT THE END OF EACH WORK SHIFT, & THE PLATES OR PATCH MAINTAINED UNTIL FULL PAVEMENT RESTORATION IS MADE W/HMAC. COLD PATCH (IF USED) SHALL BE REPLACED WITH HOT MIX HMAC WITHIN FIVE CALENDAR DAYS OR AS DIRECTED BY THE DISTRICT MANAGER OR REPRESENTATIVE IN WRITING.
4. HMAC SHALL BE A COMMERCIALY PRODUCED PLANT MIXTURE CONFORMING TO ODOT STANDARDS ("B" OR "C" DESIGNATION REFERS TO AGGREGATE SIZE ONLY).
5. 48" MINIMUM COVER IS REQUIRED FOR ALL GAS, ELECTRIC, TELEPHONE, FIBER OPTIC AND OTHER POTENTIALLY DANGEROUS/HIGH IMPACT UTILITY FACILITIES, ALL OTHER FACILITIES REQUIRE 36" MINIMUM COVER DEPTH.

LAST REVISION DATE: JULY 2015	
<b>ODOT TRENCH CROSSING, TRENCH BACKFILL &amp; SURFACE RESTORATION</b> (NTS)	
SILVERTON, OR	DETAIL NO. 302D